

Attorney Docket 55434US002  
Serial No. 09/591,584

- Sub C1  
Cont  
B1  
Cont
- (c) at least one additional lamina comprised of optically clear flexible nonadhesive polymeric material;
  - (d) a sufficient number of layers of in situ optically clear pressure sensitive adhesive layers to directly bond said laminae together with the hard coating exposed; and
  - (e) a layer of in situ optically clear ambient temperature attachable pressure sensitive adhesive to bond said laminate to window glass.

7. (Twice-Amended) The laminate of claim 1 wherein once attached to tempered or laminated window glass provides a glazing element which passes at least one of the following ANSI Z-26 tests:

- B2
- 5.04 – Two Hour Boiling Water;
  - 5.13 – Thirty Foot Ball (9.14 m) Drop;
  - 5.17 – Resistance to Abrasion;
  - 5.19 – Chemical Resistance; and
  - 5.23 – Flammability.

12. (Twice-Amended) An optically clear laminate comprising the following components adhered together in the following order:

- B3  
Sub C3
- (a) a scratch-resistant hard coat comprised of cured ceramer;
  - (b) a first biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm);
  - (c) a first pressure sensitive adhesive layer;
  - (d) a second biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm);
  - (e) a second pressure sensitive adhesive layer;
  - (f) a third biaxially oriented polyester film having a thickness of not more than 5 mils (0.13 mm); and